

ANDES TWEED WOOLEN SPUN 1/4 | 2/4^{NEW}

COMPOSITION 60% Alpaca / 40% Merino Wool (21.5 mic.)	NM 1/4 2/4
---	------------------------

Natural Color Card CCQ3 10 CCR0 CCQ9 GYC2 CCR1 75 CCR7	Color Card CCT1 CCR5 CCQ6 CCQ5 CCR3 CCQ7 CCQ4 CCR6 CCS9 CCT2 CCT0 CCR4
---	---



PRESENTATION

Cone
1 kg

* All colors available in 1 ply for twisting

INDUSTRIAL FINISHING Machine wash, using wool cycle and low speed. To avoid felting, temperature should not exceed 45°C *9 - minute wash cycle. Rapid impeller movements for 15 seconds followed by 5-second rest periods. After centrifugation, dry at 80°C. Note: Do not overload the machine with garment pieces.	COLORS AVAILABLE MINIMUM QUANTITIES PER COLOR > Refer to Color Card NM 1/4 1 Kg NM 2/4 6 kg *For 2/4 delivery 2 weeks	STOCK SAMPLING (quick delivery) > Swatch color CCT2
--	--	---

CARE INSTRUCTION

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	4	3	4
Dark	4	3	3/4

TECHNICAL INFORMATION Dyeing method tops Knot type splicer Pilling 3	KETTLE SIZE (Kg.) 200	SUGGESTED GAUGE Multi Gauge 3.5,2	CERTIFICATION CONFIDENCE IN TEXTILES STANDARD 100 16.HPE.92779 HOHENSTEIN HTTI Tested for harmful substances. www.oeko-tex.com/standard100
--	---------------------------------	--	---

- NOTES:**
- Might occur bleeding in design with white stripes and intense colors.
 - Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
 - Minimum for dark colors subject to revision.