



Awi

COMPOSITION

70% Royal Alpaca /  
30% Extra Fine Merino Wool  
(19.5 mic.)

COUNT NM

2/28 | 3 x 2/28

COLORS

40	3968	K173
23	9838	5572
43	3988	0767
2976	T300	S719*

\* Stock Sampling

COLORS AVAILABLE

MINIMUM QUANTITIES PER COLOR

STOCK SAMPLING

(quick delivery)

MINIMUM FOR SAMPLING

>	Raw white	20Kg
	Solid colors	20kg
	Melange colors	50kg
>	Swatch color	S719
>	Raw white	10Kg
	Solid colors	10kg
	Melange colors	30kg

INDUSTRIAL FINISHING

After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

CARE INSTRUCTION

Any solvent  
except  
tetrachlorethylene

Iron low

Do not bleach

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	3/4	4
Medium	3/4	3	3/4
Dark	3	2/3	3

FALL / WINTER COLLECTION 26/27 / **SIGNATURE** / Awi

TECHNICAL INFORMATION	KETTLE SIZE (Kg.)	SUGGESTED GAUGE
Dyeing method    hanks/tops	hanks                    tops	
Knot type                    splicer	20            70            50	NM 2/28: 14g
Pilling                                    3.5	30            100	NM 3x2/28: 5gg
	35            205	
	40	

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- Minimum for dark colors subject to revision.
- For solid dark shades, the fastness value could be lower than the one mentioned above. For more information contact your sales executive.