


Fall Winter 25/26 | Legacy | Coa I Coa Brushed New

COA I COA BRUSHED

NM

1/4 | 1/4.2







* Stock Sampling

INDUSTRIAL FINISHING We recommend washing at 35° in gentle cycle during 3 minutes using a softener that does not exceed 4% of the	COLORS AVAILABLE MINIMUM QUANTITIES PER COLOR STOCK SAMPLING	>	Raw white All colors Swatch color	50Kg 50kg YA43	
weight of the material considerig the finishing expected. Centrifuge for 2 minutes. Dry. Use manual iron, If a more pronounced pile is required, washing time or washing cycle revolutions should be increased, but the bath temperature	(quick delivery) MINIMUM FOR SAMPLING	>	All colors	30kg	
must be reduced to avoid the felting effect.					

							ESS (AVERAGE VALU	,
\overline{P}		\times				Dry rubbing	Wet rubbing	Wash fastness
		Δ			Light	4/5	4/5	4/5
Hand wash Any solvent	Iron low Do r	not bleach	Dry flat		Medium	4	3	4
except tetrachiorethylene					Dark	3	2/3	3
TECHNICAL	KE	ETTLE SIZE ((Kg.)		SUGGESTED	GAUGE		ERTIFICATION
INFORMATION Dyeing method tops	KE	50	(Kg.)			GAUGE	O	EKO-TEX®
INFORMATION	KE		(Kg.)		SUGGESTED	GAUGE	O STA	EKO-TEX®

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.