

Fall Winter 25/26 | Signature | Illa / Illa Brushed New

## ILLA / ILLA BRUSHED





## INDUSTRIAL FINISHING

T060

2955

We recommend washing at  $35^{\circ}$  in gentle cycle during 3 minutes using a softener that does not exceed 4% of the weight of the material considerig the finishing expected. Centrifuge for 2 minutes. Dry. Use manual iron, If a more pronounced pile is required, washing time or washing cycle revolutions should be increased, but the bath temperature must be reduced to avoid the felting effect.

COLORS AVAILABLE MINIMUM QUANTITIES PER COLOR	>	All colors	30kg
STOCK SAMPLING (quick delivery)	>	Swatch color	T246
MINIMUM FOR SAMPLING (special blends)	>	All colors	20kg

CARE INSTRUCTION		C	OLOR FASTNES	S (AVERAGE VALL	JES)
Hand wash Any solvent except tetrachiorethylene	not bleach Dry flat	Di Light Medium Dark	ry rubbing 4 3/4 3	Wet rubbing 3/4 3 2/3	Wash fastness 3/4 3 3
TECHNICAL INFORMATION	KETTLE SIZE (Kg.	.)		SUGGESTED	GAUGE
Dyeing method hanks Knot type knot Pilling 3	50 100 200			5gg	

## NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.