

Fall Winter 25/26 | Stock Service Tejido Industrial | Essentials Vibes | Muhu 2/28

MUHU 2/28







INDUSTRIAL FINISHING

- After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

COLORS AVAILABLE

Refer to Stock Service Color Card



NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- Minimum for dark colors subject to revision.