


MAJESTIC

COMPOSITION 100% Imperial Alpaca	NM 2/40
--	-------------------

Color Card

L815	Q490
T246	1637
1367	W602
2414	6416
T877*	4464
2955	T060



PRESENTATION

Cone
1 kg

* Stock Sampling

<p>INDUSTRIAL FINISHING</p> <p>After Knitted process stabilize the panel by steaming or immersing in hot water, cooling then off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.</p>	<p>COLORS AVAILABLE</p> <p>MINIMUM QUANTITIES PER COLOR</p>	>	<p>Raw white 30kg</p> <p>Solid color 30kg</p> <p>Melange colors 50kg</p>
	<p>STOCK SAMPLING</p> <p>(quick delivery)</p>	>	<p>Swatch color T877</p>
	<p>MINIMUM FOR SAMPLING</p> <p>(special blends)</p>	>	<p>Raw white 10kg</p> <p>Solid color 10kg</p> <p>Melange colors 30kg</p>

CARE INSTRUCTION

Any solvent except tetrachlorethylene	Iron low	Do not bleach

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	3/4	3/4	3/4
Dark	3/4	2/3	3

<p>TECHNICAL INFORMATION</p> <p>Dyeing method hanks</p> <p>Knot type splicer</p> <p>Pilling 3.5</p>	<p>KETTLE SIZE (Kg.)</p> <p>30</p> <p>40</p> <p>80</p> <p>200</p>	<p>SUGGESTED GAUGE</p> <p>14gg</p>	<p>CERTIFICATION</p> <p>16.HPE.92779 HOHENSTEIN HTTI</p> <p>Tested for harmful substances. www.oeko-tex.com/standard100</p>
--	--	---	--

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.