

MERINO SOFT

COMPOSITION

40% Baby Alpaca /
60% Merino Wool
(21.5 mic.)


NM

2/28

Natural Color Card



RW001 RW009



RW002 RW006



RW003* RW007




RW004 RW008

Color Card



T641 B780 2468




0665* B987 5313



S893 B501 J405



I646 2433 7870



PRESENTATION



Cone
1 kg

* Stock Sampling

INDUSTRIAL FINISHING

After Knitted process stabilize the panel by steaming or immersing in hot water, cooling then off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

**COLORS AVAILABLE
MINIMUM QUANTITIES PER COLOR**

**STOCK SAMPLING
(quick delivery)**

MINIMUM FOR SAMPLING

| | | |
|---|------------------------|--------------|
| > | Ecru and natural shade | 30kg |
| > | Solid color | 30kg |
| > | Heather shades | 50kg |
| > | Swatch color | 0665 - RW003 |
| > | Ecru | 10kg |
| > | Solid color | 20kg |
| > | Heather shades | 20kg |

CARE INSTRUCTION



Hand wash



Any solvent
except
tetrachlorethylene



Iron low



Do not bleach



Dry flat

COLOR FASTNESS (AVERAGE VALUES)

| | Dry rubbing | Wet rubbing | Wash fastness |
|--------|-------------|-------------|---------------|
| Light | 4/5 | 4/5 | 4/5 |
| Medium | 4 | 3 | 4 |
| Dark | 4 | 3/4 | 4 |

TECHNICAL INFORMATION

| | |
|---------------|---------|
| Dyeing method | hanks |
| Knot type | splicer |
| Pilling | 3 |

KETTLE SIZE (Kg.)

| |
|-----|
| 30 |
| 40 |
| 80 |
| 200 |

SUGGESTED GAUGE

12 gg

CERTIFICATION



NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.