

Fall Winter 25/26 | Stock Service Tejido Industrial | Essentials Vibes | Muhu / Anta

MUHU / ANTA



NM 2/16







INDUSTRIAL FINISHING

1107

1002

1391

1801

1799

8316

0785

0574

3709

- After knitted process stabilize the panel by steaming or immersing in hot water, cooling them off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

COLORS AVAILABLE

Refer to Stock Service Color Card

CARE INSTRUCTION











COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	4	4
Medium	4	3	4
Dark	3	2/3	3

TECHNICAL INFORMATION Hanks/Tops Dyeing method Knot type Splicer Pilling 3.5

KETTLE SIZE (Kg.) 30 40 80 200

SUGGESTED GAUGE

7gg - 10gg

CERTIFICATION **OEKO-TEX**® STANDARD 100

16.HPE.92779 HOHENSTEIN HTTI

Tested for harmful substances.
www.oeko-tex.com/standard100

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- Minimum for dark colors subject to revision.