

FALL / WINTER COLLECTION 26/27 / SHADES OF THE ANDES / Muhu



INDUSTRIAL FINISHING

After knitted process stabilize the panel by steaming or immersing in hot water, cooling them Off in water and softening at 30 degrees using the products Of gour choice on a delicate-fabrics wash cgcle; then it Should be given another spin. you may need to accommodate the fabric after spinning; this Should be done with a manual steam iron before starting the drying process.

CARE INSTRUCTION



TECHNICAL INFORMATION



NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- Minimum for dark colors subject to revision.
- For solid dark shades, the fastness value could be lower than the one mentioned above. For more information contact your sales executive.

INTIFIL SA Sonnenrainweg 8 - 8834 Schindellegi - Switzerland | Phone: +41 79 335 25 00 | Email: info@intifil.com www.intifil.com