

PISKU^{NEW}

COMPOSITION

80% Suri Alpaca /
20% Pima Cotton

NM

1/3.5

Color Card



* Stock Sampling



PRESENTATION



Cone
1 kg

INDUSTRIAL FINISHING

We recommend washing at 35° in gentle cycle during 3 minutes using a softener that does not exceed 4% of the weight of the material considering the finishing expected. Centrifuge for 2 minutes. Dry. Use manual iron, if a more pronounced pile is required, washing time or washing cycle revolutions should be increased, but the bath temperature must be reduced to avoid the felting effect.

**COLORS AVAILABLE
MINIMUM QUANTITIES PER COLOR**

Raw white 50Kg
All colors 50kg

**STOCK SAMPLING
(quick delivery)**

Swatch color W515

MINIMUM FOR SAMPLING

All colors 30kg

CARE INSTRUCTION



Hand wash



Any solvent
except
tetrachlorethylene



Iron low



Do not bleach



Dry flat

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4/5	4/5	4/5
Medium	4	3	4
Dark	3	2/3	3

**TECHNICAL
INFORMATION**

Dyeing method hanks
Knot type knot
Pilling 3

KETTLE SIZE (Kg.)

50
100
200

SUGGESTED GAUGE

3gg

CERTIFICATION



NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.