

Tacama 70

COMPOSITION
70% Organic Cotton /
30% Superfine Alpaca

COUNT NM
2/34

Natural Color Card



ES001



ES003*



AC70



AC75



W510



AC85**



AC91**



ES008



ES005



AC71



AC76



W511*



AC88**



AC92**



ES010



ES006



AC72



W505



AC82



AC89*



AC97**



AC73



W504



AC83



AC90**



AC96**



AC74



AC79



AC84



AC87**



AC94**

Color Card

PRESENTATION



Cone
1 kg

*Stock Sampling
** Delave Effect

COLORS AVAILABLE
MINIMUM QUANTITIES PER COLOR

STOCK SAMPLING
(quick delivery)

MINIMUM FOR SAMPLING
(special blends)

- >






Raw white30Kg
Natural Shades50Kg
Heather Shades30Kg
- >

Swatch colorW511 - AC89 - ES003
- >

Raw White10Kg
Natural Shades20Kg
Heather shades20Kg

INDUSTRIAL FINISHING

After Knitted process stabilize the panel by steaming or immersing in hot water, cooling then off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

CARE INSTRUCTION		COLOR FASTNESS (AVERAGE VALUES)		
 Hand wash	 Any solvent except tetrachlorethylene	 Iron low	 Do not bleach	 Dry flat
		Dry rubbing	Wet rubbing	Wash fastness
Light		4	3/4	4
Medium		3/4	2/3	3/4
Dark		3	2/3	3

TECHNICAL INFORMATION	KETTLE SIZE (Kg.)	SUGGESTED GAUGE
Dyeing Method hanks	30 75	14gg
Knot type splicer	35 150	
Pilling 3.5	40	

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors.
- Minimum for dark colors subject to revision.
- For solid dark shades, the fastness value could be lower than the one mentioned above. For more information contact your sales executive.