


TACAMA 70


COMPOSITION
70% Organic Cotton /
30% Superfine Alpaca

NM
2/34

Natural Color Card



Color Card



PRESENTATION

Cone
1 kg

* Stock Sampling

INDUSTRIAL FINISHING

After Knitted process stabilize the panel by steaming or immersing in hot water, cooling then off in water, and softening at 30 degrees using the products of your choice on a delicate-fabrics wash cycle; then it should be given another spin. You may need to accommodate the fabric after spinning; this should be done with a manual steam iron before starting the drying process.

**COLORS AVAILABLE
MINIMUM QUANTITIES PER COLOR**

**STOCK SAMPLING
(quick delivery)**

MINIMUM FOR SAMPLING

>	Ecru and natural shade	30kg
>	Solid color	40kg
>	Heather shades	40kg
>	Swatch color	W505 - ES003
>	Ecru	10kg
>	Solid color	20kg
>	Heather shades	20kg

CARE INSTRUCTION



Hand wash



Any solvent
except
tetrachlorethylene



Iron low



Do not bleach



Dry flat

COLOR FASTNESS (AVERAGE VALUES)

	Dry rubbing	Wet rubbing	Wash fastness
Light	4	3/4	4
Medium	4	3	3/4
Dark	3	2/3	3

TECHNICAL INFORMATION

Dyeing method	hanks
Knot type	splicer
Pilling	3.5

KETTLE SIZE (Kg.)

30
40
80
200

SUGGESTED GAUGE

12gg ~ 14gg

NOTES:

- Might occur bleeding in design with white stripes and intense colors.
- Consult our sales team about dyeing process that decrease bleeding risk on intense colors
- Minimum for dark colors subject to revision.